

SUPA 75[®] Alloy Slicklines for Highly Corrosive Well Media.

Material grade UNS N 08926

SUPA 75^{$^{(R)}$} offers extremely high stability against corrosion, stress corrosion & inter-granular corrosion in wells where CO₂, H₂S and Chlorides are present.

Density

Modulus of Elasticity

Maximum Temperature

Typical Physical Properties

PREN= 42 TO 47 (PREN=%Cr + 3.3 x %Mo + 16%N)

8.1g/cc

160GPA

260*C

Chemica	Chemical Composition Range				
Element	Min	Max			
Ni	24.0	26.0			
Cr	20.0	21.0			
Mo	6.0	6.8			
Si	N/A	0.5			
Mn	N/A	2.0			
Cu	0.5	1.0			
Ν	0.15	0.25			
С	N/A	0.02			
Р	N/A	0.03			
S	N/A	0.005			

S	N/A	0.005		
			-	
	Mech	nanical Proper	ties	
Diameter	Nom. B. Load**	Approx. Weight	Min. Pulley Diameter	Stretch*
Ins.	Lbs.	Lbs./1000ft	Ins	ft / 1000 ft / 1000 lb
0.092	1620	23	11	7
0.108	2170	32	13	5
0.125	2900	43	15	4
0.140	3400	54	17	TBA
0.160	4400	71	20	TBA

SUPA 75[®] is a Super-Austenitic stainless alloy. It is well suited for work in highly corrosive wells especially where pitting, crevice corrosion, and stress corrosion cracking are likely to occur. Increased levels of chromium and nickel ensure excellent general corrosion resistance whilst nitrogen content increases tensile and yield strength.

*Weight for stretch calculation must include the weight of the wire.

**DWS recommends a maximum safe working load of 60% Actual Breaking Load (ABL) when jarring and 70% ABL for straight pulls.



A "ONE STOP" SOURCE FOR SLICKLINES, BRAIDED STRANDS & DOWN-HOLE TOOLS

Unit 12, Bullrush Business Park Bullrush Grove, Doncaster, DN4 8SL, U.K. **Tel:** +44 (0)1302 349 419 www.danumwellservices.com Email: sales@danumwellservices.com ISO 9001:2015 Company Registration NO: Eng. 3788445 VAT No: GB 73 75 76 983

Whilst every effort has been made to ensure the information is correct, Danum Well Services Ltd will not accept and responsibility for any errors or misinterpretation of the information. Danum Well Services Ltd reserves the right to change information without prior notification.